

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106  
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

**Client :** Premium Floors Australia  
7/14 Rodborough Road  
Frenchs Forest NSW 2086

**Test Number :** 18-006770  
**Issue Date :** 5/03/2019  
**Print Date :** 5/03/2019  
**Order Number :** READCORK AMBIENT

**Sample Description** Clients Ref : "Readycork ambient engineered cork  
Engineered Flooring  
End Use : Flooring  
Nominal Composition : Cork  
Nominal Mass per Unit Area/Density : Approx 7.9 g/m<sup>2</sup>  
Nominal Thickness : 10.5mm

### AS/ISO 9239.1-2003

#### Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 19/11/2018  
Date Tested 04/03/2019

CHF Value	1	2	3	Mean
Non Directional	7.1	7.7	7.3	7.4 kW/m <sup>2</sup>
Smoke Value	1	2	3	Mean
Non Directional	14	33	19	22 %min

Observations :  
Transitory flaming Yes

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Each specimen was clamped to a substrate of 6mm thick fibre reinforced cement board prior to testing.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

158410

32263

Page 1 of 1

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing  
- Chemical Testing : Accreditation No. 983  
- Mechanical Testing : Accreditation No. 985  
- Performance & Approvals Testing : Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR