

DIMENSIONS

Length	1261mm
Width	192mm
Thickness	7mm
Number of panels per pack	10
m ² per pack	2.421m ²
Bevels	Nil bevel
Joining System	Uniclic®

FACTORY WARRANTY

	METHOD	PARAMETERS	NORM REQUIREMENTS	CLIX VALUES
Usage class	EN 13329			Class 32
Warranty	Residential use	See warranty conditions See warranty conditions	See warranty conditions See warranty conditions	25-year Structural warranty 15-year Wear warranty

GENERAL DATA

	METHOD	PARAMETERS	NORM REQUIREMENTS	CLIX VALUES
Wear resistance	EN 13329		>4,000 cycles	With overlay Class 32
Wear class	EN 13329		AC4	With overlay AC4
Impact resistance	EN 13329		IC2	IC2
Scratch resistance	EN 438-2:25		Charge ≥ 3N	Charge ≥ 5N
Effect of a castor chair	ISO 4918 (with underlay)	Type W (EN 12529)	25,000 cycles	No change
Thickness swelling	ISO 24336	After 24hr immersion at 20°C	≤ 18%	≤ 12%
Locking strength	ISO 24334	F10.2 long side	≥ 1 kN/m	≥ 1 kN/m
		Fmax long side		≥ 1 kN/m
		Fs0.2 short side	≥ 2 kN/m	≥ 2 kN/m
		Fmax short side		≥ 2 kN/m
Effect of furniture leg	EN 424		No damage shall be visible, when tested with foot type 0	No visible Damage
Surface soundness	EN 13329	N/mm ²	≥ 1.25	≥ 1.50
Static indentation	EN 433	Residual indentation	≤ 0.05mm	No visible change
Resistance to staining	EN 438	Group 1, 2	Class 5	Class 5
		Group 3	Class 4	Class 5
		Height difference	≤ 0.15mm	≤ 0.10mm
General appearance	EN 13329	Opening between joints	≤ 0.20mm	≤ 0.10mm
		Cupping in the length	concave ≤ 0.50% convex ≤ 1.0%	≤ 0.50% ≤ 1.0%
		Cupping in the width	concave ≤ 0.15% convex ≤ 0.20%	≤ 0.15% ≤ 0.20%
Dimensional variations after changes in relative humidity	EN 13329	δl	δl average ≤ 0.9mm	≤ 0.9mm
		δw	δw average ≤ 0.9mm	≤ 0.9mm
Light fastness	EN ISO 105 B02	Blue reference	Class > 6	Class 8

OTHER TECHNICAL DATA

	METHOD	PARAMETERS	NORM REQUIREMENTS	CLIX VALUES
Burning cigarette	EN 438-2:30		Class 4	Class 5



ENVIRONMENT, SAFETY & HEALTH

	METHOD	PARAMETERS	NORM REQUIREMENTS	CLIX VALUES
Formaldehyde emission	EN 717-1	ppm (large chamber)	E1 < 0.1	< 0.01
Anti-static	En 1815		≤ 2.0 kV	≤ 2.0 kV
Reaction to fire	AS/ISO 9239.1	Class		5.6 kW/m ² / Smoke 10%
Thermal resistance	EN 12996:2001	m ² K/W	With underlay	0.09 m ² K/W
Floor heating		On recommended underlay	See special installation instructions	Suitable
Slip resistance	AS 4586	Pendulum test		P3

