

LAMINATE

Quick-Step Perspective Nature

Valid from: 02:2021
Subject to change without notification

DIMENSIONS

| | |
|---------------------------|---------------------------------|
| Width | 212mm |
| Length | 1380mm |
| Number of panels per pack | 7 |
| m ² per pack | 2.048m ² |
| Bevels | Impression edge (bevel) 4 sides |
| Thickness | 9mm |
| Joining system | Uniclic |
| Water damage warranty | 10 year waterproof surface |



FACTORY WARRANTY

| | METHOD | PARAMETERS | NORM REQUIREMENTS | QUICK-STEP VALUES |
|-------------|-----------------|-------------------------|-------------------------|---|
| Usage class | EN 13329 | | | Class 32 |
| Warranty | Residential use | See warranty conditions | See warranty conditions | 25 year Wear warranty |
| | | See warranty conditions | See warranty conditions | 10 year Waterproof surface |
| | Commercial use | See warranty conditions | See warranty conditions | 5 year Waterproof surface Wear warranty on Application |

GENERAL DATA

| | METHOD | PARAMETERS | NORM REQUIREMENTS | QUICK-STEP VALUES |
|---|--------------------------|------------------------------|--|-----------------------|
| Wear resistance | EN 13329 | | ≥4,000 cycles | With overlay Class 32 |
| Wear class | EN 13329 | | AC4 | With overlay AC4 |
| Impact resistance | EN 13329 | | IC2 | IC2 |
| Scratch resistance | EN 438-2:25 | | Charge ≥ 3N | Charge ≥ 5N |
| Effect of a castor chair | ISO 4918 (with underlay) | Type W (EN 12529) | 25,000 cycles | No change |
| Thickness swelling | ISO 24336 | After 24hr immersion at 20°C | ≤ 18% | ≤ 12% |
| Locking strength | ISO 24334 | F10.2 long side | ≥ 1 kN/m | ≥ 1 kN/m |
| | | Fmax long side | | ≥ 1 kN/m |
| | | Fs0.2 short side | ≥ 2 kN/m | ≥ 2 kN/m |
| | | Fmax short side | | ≥ 2 kN/m |
| Effect of furniture leg | EN 424 | | No damage shall be visible, when tested with foot type 0 | No visible damage |
| Surface soundness | EN 13329 | N/mm ² | ≥ 1.25 | ≥ 1.50 |
| Static indentation | EN 24343-1 | Residual indentation | ≤ 0.05mm | No visible change |
| Resistance to staining | EN 438 | Group 1, 2 | Class 5 | Class 5 |
| | | Group 3 | Class 4 | Class 5 |
| General appearance | EN 13329 | Height difference | ≤ 0.15mm | ≤ 0.10mm |
| | | Opening between joints | ≤ 0.20mm | ≤ 0.10mm |
| | | Cupping in the length | concave ≤ 0.50% | ≤ 0.50% |
| | | | convex ≤ 1.0% | ≤ 1.0% |
| | | Cupping in the width | concave ≤ 0.15% | ≤ 0.15% |
| convex ≤ 0.20% | ≤ 0.20% | | | |
| Dimensional variations after changes in relative humidity | EN 13329 | δl | δl average ≤ 0.9mm | ≤ 0.9mm |
| | | δw | δw average ≤ 0.9mm | ≤ 0.9mm |
| Light fastness | EN ISO 105 B02 | Blue reference | Class > 6 | Class 8 |

OTHER TECHNICAL DATA

| | METHOD | PARAMETERS | NORM REQUIREMENTS | QUICK-STEP VALUES |
|-------------------|-------------|------------|-------------------|-------------------|
| Burning cigarette | EN 438-2:30 | | Class 4 | Class 5 |



LAMINATE

Quick-Step Perspective Nature

Valid from: 02:2021
Subject to change without notification

ENVIRONMENT, SAFETY & HEALTH

| | METHOD | PARAMETERS | NORM REQUIREMENTS | QUICK-STEP VALUES |
|-----------------------|---------------|------------------------|---------------------------------------|---------------------------------|
| Formaldehyde emission | EN 717-1 | ppm (large chamber) | E1 < 0.1 | < 0.01 |
| Anti-static | EN 1815 | | ≤ 2.0 kV | ≤ 2.0 kV |
| Reaction to fire | AS/ISO 9239.1 | Class | | 5.6kW/m ² /Smoke 10% |
| Thermal resistance | EN 12996:2001 | m ² K/W | | 0.059m ² K/W |
| Floor heating | | On Quick-Step underlay | See special installation instructions | Suitable |
| Slip resistance | AS 4586 | Pendulum test | | P1 – Waxed Oak |
| | AS 4586 | Pendulum test | | P1 – Painted Oak |
| | AS 4586 | Pendulum test | | P2 – Merbau |
| | AS 4586 | Pendulum test | | P3 - Soft Patina Oak |
| | AS 4586 | Pendulum test | | P3 – Patina Oak |
| | AS 4586 | Pendulum test | | P4 – Brushed Oak |

CERTIFICATES

| | |
|----------------------|---------------|
| U-zeichen | z-156.606-996 |
| AFFSET | A+ |
| Nordic ecolabel | 30290001 |
| PEFC | PEFC/07-32-37 |
| Singapore Greenlabel | 035-098-1422 |
| M1 | |

