Technical Data Sheet
Quick-Step Faro

Valid from: 06:2025

Subject to change without notification

General Data

Panel	2200mm x 220mm
Total Thickness	±13mm nominal
Number of lengths per pack	4
Pack contents	Includes some shorter boards
Quantity per pack	1.936m$_2$
Pack weight	20.35kg
Quantity per pallet	123.90m^2 (64 packs)
Bevel	Long sides

Panel Build Up

Surface layer thickness	PEFC controlled sources	EN 13489	± 2.5mm nominal
Core layer thickness	PEFC controlled sources	HDF Mastercore	± 9mm nominal
Backing layer	PEFC controlled sources	Spruce	2mm
Joining system			Uniclic® 4 sides

Warranty Information

Domestic / Residential Use		25-year Residential Wear Warranty*
Uniclic® joining system		Lifetime (33 years)*
Structural warranty		Lifetime (33 years)*
Wet warranty	Provides a warranty against water damage excluding flooring or appliance failure	15-years*
Commercial warranty		On request

**Conditions apply – seek warranty terms and conditions for more information*

Surface Layer

Wood species		Oak
Origin		Europe
Finishing level		Extra matt
Finishing treatment	UV cured lacquer	7 layers of anti-scratch UV acrylic lacquer
Natural variance	As a natural product, colour, grain and level of natural features will vary from board to board and most often deviate from samples provided.	
Surface treatments	Stains, bevels and surface textures vary by product – refer to website, brochure and samples.	

Premium Floors Australia Pty Ltd – 3/35 – 45 Bend Road, Keysborough VIC 3175
Floorscape Ltd – Unit C, 19 Triton Drive, Rosedale Auckland 0632 New Zealand

Email: services.australia@unilin.com
Email: sales.floorscape@floorscape.co.nz

T +61 2 9982 3441
T +64 9 476 0428

Technical Data Sheet
Quick-Step Faro

Valid from: 06:2025

Subject to change without notification

Panel Build Up

	Surface Layer (visible elements)	
	Vibrant Grade Refers to All others	**Nature Grade** Refers to FAR5411WL & FAR6912WL
Sound sapwood	Permitted, colour stained	Permitted, colour stained
Knot size (EN1310/AS2796)	≤ 80mm	≤ 20mm
Knot frequency	Unlimited	≤ 3 per lm
Knot filling	Half or fully filled	Fully filled
Checks/Cracks	Permitted if closed crack ≤ ½ the pack length	Not Permitted
Bark pockets	Not permitted	Not permitted
Grain structure	Unlimited	Light to Moderate Variation
Colour variation	Lively variation	Light to Moderate
Medullary ray	Permitted	Permitted
	Core Layer and Backing Layer (non-visible elements)	

All features permitted (no limitation) as to size or quantity if these do not impair the strength or quality of the parquet flooring.

Installation		Standard / Norm requirements	Quick-Step values
Floating Installation	Always install on Quick-Step Underlay in accordance with the Installation Instructions		
Direct Stick Installation	Always install using Quick-Step MS Polymer in accordance with the Quick-Step Direct Stick Installation Instructions		
Machining tolerances	Lipping between boards- difference in height at joins (mm)		≤ 0.20
	Difference in board width (mm) – (EN13489)	≤ 0.20	≤ 0.15
	Cupping across width of board % - (EN13489)	≤ 0.20	≤ 0.20
Dimensional stability	Cupping short side max % - (ISO 24339)	≤ 0.30	≤ 0.25
	Cupping short side min % - (ISO 24339) Changes 30 – 85 % RH	≥ 0.20	≥ 0.15
	Open joints short side join (mm) – (ISO 24339)	≤ 0.20	≤ 0.15
	Open joints long side join (mm) – (ISO 24339)	≤ 0.30	≤ 0.20
Underfloor heating	European Oak is suitable for floating installation as well as direct stick over underfloor heating. Please see special installation instructions for Quick-Step floors over heated sub-floors.		

Premium Floors Australia Pty Ltd – 3/35 – 45 Bend Road, Keysborough VIC 3175
Floorscape Ltd – Unit C, 19 Triton Drive, Rosedale Auckland 0632 New Zealand

Email: services.australia@unilin.com
Email: sales.floorscape@floorscape.co.nz

T +61 2 9982 3441
T +64 9 476 0428

Technical Data Sheet

Quick-Step Faro

Valid from: 06:2025

Subject to change without notification

Technical Performance

Wear resistance	DIN 68861	S33		>550 cycles
Stain resistance	EN 13442			Class 5
			Blue ink	Class 3
CE	EN 14342:2013	Notified body	0766 EPH Dresden	DOP QW 0507
Castor chairs	ISO 4918	Tested with underlay		25.000
Slip resistance	AS4586	Pendulum test		P4 Extra Matt
Emission of formaldehyde	EN 717-1	Large Chamber		≤ E1
PCP	CEN/TR 14823:2004			≤ 5 ppm
Heat resistance	EN 12664: 2001			0,14 m².K/W
Reaction to fire	ISO 9239.1			5.6 kW/m² / 11% smoke

Environmental Certificates

AFFSET	A	France
PEFC	PEFC/07-32-37	
EPD	Available on request	

Premium Floors Australia Pty Ltd – 3/35 – 45 Bend Road, Keysborough VIC 3175
Floorscape Ltd – Unit C, 19 Triton Drive, Rosedale Auckland 0632 New Zealand

Email: services.australia@unilin.com
Email: sales.floorscape@floorscape.co.nz

T +61 2 9982 3441
T +64 9 476 0428