



# Technical Data Sheet

## Quick-Step Massimo

Valid from: 05:2021

Subject to change without notification

### General Data

Panel	2400mm x 260mm
Total Thickness	14mm nominal
Number of panels per pack	4 planks
Nested lengths	Up to 2 shorter panels per pack
Quantity per pack	2.496m <sup>2</sup>
Weight per pack	23.48kg
Quantity per pallet	99.84m <sup>2</sup> (40 Packs)

### Panel Build Up

Surface layer thickness	PEFC controlled sources	EN 13489	± 3mm nominal
Core layer thickness		Hevea (with HDF ends)	± 9mm nominal
Backing layer	PEFC controlled sources	Spruce	2mm
Joining system			Uniclic Multifit

### Warranty Information

Domestic / Residential Use		25 Year Residential Wear Warranty*
Uniclic Multifit joining system		Lifetime
Structural Warranty		Lifetime*
Commercial Warranty		On request
Edge Protect +	Provides a warranty against moisture staining along the board's edges	10 years*
Surface & Edge Protect + (lacquered products only)	Provides a warranty against dirt trapped within the surface coating of a board	10 years*

\*Conditions apply – seek warranty terms and conditions for more information

### Surface Layer

Wood species	Oak
Origin	Europe
Finishing	UV cured lacquer 5 – 7 layers
Natural variance	As a natural product, colour, grain and level of natural features will vary from board to board and most often deviate from samples provided
Surface treatments	Stains, bevels and surface textures vary by product – refer to website, brochure and samples



# Technical Data Sheet

## Quick-Step Massimo

Valid from: 05:2021

Subject to change without notification

### Grading of Timber Elements

Grading Standard used - EN 13489:2002 Free Class (unless otherwise specified)

Surface Layer (visible elements)	
Vibrant Grade	
Sound sapwood	Permitted, colour stained
Knot size (EN1310)	Permitted maximum 80mm
Knot frequency	Unlimited
Knot filling	Half or fully filled
Checks/Cracks	Permitted unlimited
Bark pockets	Not permitted
Grain structure	Unlimited
Colour variation	Very lively variation
Medullary ray	Permitted
Core Layer and Backing Layer (non-visible elements)	

All features permitted (no limitation) as to size or quantity if these do not impair the strength or quality of the parquet flooring

Installation	Standard / Norm requirements	Quick-Step values
Floating Installation	Always install on Quick-Step Underlay in accordance with the Installation Instructions	
Direct Stick Installation	Always install using Quick-Step Parquet Adhesive in accordance with the Direct Stick Installation Instructions	
Machining tolerances	Lipping between boards- difference in height at joins (mm)	≤ 0.50mm
	Difference in board width (mm) – (EN13489)	≤ 0.20      ≤ 0.15
	Cupping across width of board % - (EN13489)	≤ 0.2      ≤ 0.2
Dimensional stability	Cupping short side max % - (ISO 24339)	≤ 0.30      ≤ 0.25
	Cupping short side min % - (ISO 24339)	≥ - 0.20      ≥ - 0.15
	Changes 30 – 85 % RH	
	Open joints short side join (mm) – (ISO 24339)	≤ 0.20      ≤ 0.15
	Open joints long side join (mm) – (ISO 24339)	≤ 0.30      ≤ 0.20
Underfloor heating	Suitable providing adherence to special installation instructions	



# Technical Data Sheet

## Quick-Step Massimo

Valid from: 05:2021

Subject to change without notification

### Technical Performance

Wear resistance	DIN 68861	S33	>550 cycles
Stain resistance	EN 13442	Floors with Edge Protect+	All except blue ink
			Blue ink
		Floors with Surface Protect + (Lacquered only)	Class 5
CE	EN 14342:2013	Notified body	0766 EPH Dresden
Castor chairs	ISO 4918	Tested with underlay	DOP QW 0507
Slip resistance	AS4586	Pendulum test	25.000
Emission of formaldehyde	EN 717-1	Large Chamber	P3
PCP	CEN/TR 14823:2004		≤ E1
Heat resistance	EN 12664: 2001		≤ 5 ppm
Reaction to fire	ISO 9239.1		0,14 m <sup>2</sup> .K/W
			4.6 kW/m <sup>2</sup> 13%

### Environmental Certificates

AFFSET	A	France
PEFC	PEFC/07-32-37	
EPD	Available on request	

